



UV STABILIZER MASTERBATCH

SP7251 0002

Characteristics:

- PP based UV masterbatch for improved resistance to UV degradation
- It is a dispersion of polymeric HALs in PP free from mineral fillers, waxes and other lubricants

Applications:

- Tarpaulin
- Woven sack
- Green house films
- Telecommunication ducts

Material Status	:	Commercially Active
Agency Ratings	:	-----

PROPERTY	ASTM TEST METHOD	TEST CONDITION	VALUE	UNIT
Melt Flow Index	D1238	190°C/2.16kg	10	gm/10min
Density	D792	-	0.96	gm/cc
Active Content			20	%
Moisture Content	SPL	-	<0.1	%
Carrier Resin	-	-	PP	-
Compatibility	-	-	PP	-
LDR*	-	-	2-5	%

* The amount of masterbatch added depends on the performance requirements of the final application.

Method of Addition :

Grade is designed for ease of dilution and homogeneous mixing and is therefore suitable for direct addition using dosing units or by pre-blending

Typical Performance Data

Polymer	PP-40 micron thick / white with 3 % CaCO ₃ woven fabric of 800 Denier
Exposure	130 kLy / year – Weather-O-Meter in UV A & UV B lamp exposure (for 144 & 200 hrs Resp.)
Evaluation	50% retention of tensile strength
Blank PP	32 kLy
PP + 2% SP7251 0002	160 kLy

Packaging :

This product is supplied in regular pellet form packed in 25 Kg bags. SPL recommends storing of material in cool and dry place shaded from sunlight and heat.

The information contained herein is provided for general reference purposes only. By providing the information contained herein, Supreme Petrochem Ltd makes no guarantee or warranty and does not assume any liability with respect to the accuracy or completeness of such information or the product results in any specific instance and hereby expressly disclaims any implied warranties of merchantability or fitness for a particular purpose, or any other warranties or representations whatsoever, expressed or implied. Nothing contained herein shall be construed as a license to use the products of Supreme Petrochem Ltd in any manner that would infringe any patent. SPL reserves the right to review and revise the content of this catalogue.



SUPREME PETROCHEM LTD

17/18, Shah Industrial Estate,
Veera Desai Road, Andheri (W), Mumbai- 400053, India
Tel.: + 91-22-26736196 to 99, fax : +91-22-26736203

